



Plasma 12 Strand

ABS and DNV type approved sizes

Diameter	Circumference	Part Number	Approx. Weight Per 100 Ft. In LBS	Minimum Tensile Strength In LBS**
1-1/8"	3-1/2"	800-10290	31.9	147,000
1-1/4"	3-3/4"	800-10300	36.2	165,000
1-5/8"	5"	800-10400	66	291,000
1-3/4"	5-1/2"	800-10500	78	314,000
2"	6"	800-10600	91	355,000
2-1/8"	6-1/2"	800-0	109	428,000
2-1/4"	7"	800-0	122	481,000
2-1/2"	7-1/2"	800-0	148	530,000
2-5/8"	8"	800-0	167	596,000
2-3/4"	8-1/2"	800-0	187	660,000
3"	9"	800-0	214	780,000
3-1/8"	9-1/2"	800-0	235	850,000
3-1/4"	10"	800-0	261	940,000
3-1/2"	10-1/2"	800-0	298	1,108,000
3-5/8"	11"	800-0	324	1,250,000
3-3/4"	11-1/2"	800-0	343	1,317,000
4"	12"	800-0	394	1,520,000

**Tensile Strengths are determined in accordance with Cordage Institute 1500.2. Test Methods for Fiber Rope. Minimum Tensile Strength (MTS) published assumes spliced eye termination at each end of the rope.